




Planeo 4088



19 ³/₄ in x 2 ¹/₄ in or 500 mm x 60 mm

Technical datasheet




Planeo 4088

WHS: Wood hybrid system

Geolam[®]

Architectural Eco-Technology



Section tolerances in mm: +/- 2.0 mm or +/- 3/32 in

The outer wpc layer is sanded. The provided dimensions are average thickness (as well for all drawing in that document)

Fire rating:

On request:

ASTM E-84 class A

Euroclass NF EN 135011 : B, s3-d0

Euroclass NF EN 135011 : A2, s3-d0

NFP 92 -507 : M2 or M1

Surfaces finish: Sanded

Other surface textures available on request. Sanding finish and/or shading may vary between runs. WPC thickness may vary in compliance with flame test requirements.

Profiles fastening and installation: Planeo boards cannot be cut within the bolts at either board end. Refer to our website www.geolam.com

Technical information may change without warning.

Standard length: 9 ft 10 in | 3.0 m

On order any length from: 7 ft to 27 ft | 2.15 m to 8.25 m

Weight: 9.35 lb/ft | 13.91 kg/m

Secondary moment I_x (cm⁴): 245.35

Secondary moment I_y (cm⁴): 9217.43

Section modulus Z_{+x} (cm³): 86.09

Section modulus Z_{-x} (cm³): 86.09

Section modulus Z_{+y} (cm³): 370.92

Section modulus Z_{-y} (cm³): 370.92

Core in anodized aluminum alloy: A6063S-T5 Serie 6000

Coefficient of Thermal Expansion (20-100°C):
23.4 µm/m/°C

Modulus of Elasticity: 68.9 GPa

Max Tensile Strength: 186 Mpa

Carbon Footprint:

WPC : 1.54 kg CO₂/Kg

Profile : 9.005 kg CO₂/Kg



Teak



Limba



Rosewood



Wenge



Bilंगा




Carbon



Ivory



Any color on request



Technical specifications, dimensions in mm			Cross section coefficient Z+x (cm ³)	86.09	Wood hybrid system WHS	Type 1.0
Weight (kg/ml)			13.91	86.09	Planeo 4088	
Cross section, secondary moment Ix (cm ⁴)			245.35	Cross section coefficient Z-x (cm ³)		
Cross section, secondary moment Iy (cm ⁴)			9217.43	Cross section coefficient Z+y (cm ³)		
				370.92	Cross section coefficient Z-y (cm ³)	