



Soleo 6032



6 in x 1 ³/₄ in or 150 mm x 46 mm

Technical datasheet



Soleo 6032

WHS: Wood hybrid system

Geolam®

Architectural Eco-Technology



Section tolerances in mm: +0.5 / -2.0 mm or +1/64 to -5/64 in

The outer wpc layer is sanded for aesthetic reasons and consists of peaks and valleys; the dimension provided is average thickness

Fire rating:

On request:

ASTM E-84 class A

Euroclass NF EN 135011 : B, s3-d0

Euroclass NF EN 135011 : A2, s3-d0

NFP 92 -507 : M2 or M1

Surfaces finish: Sanded

Other surface textures available on request. Sanding finish and/or shading may vary between runs. WPC thickness may vary in compliance with flame test requirements.

Profiles fastening and installation:

Check our website www.geolam.com

Technical information may change without warning.

Standard length: 9 ft 10 in | 3.0 m

On order any length from: 7 ft to 19 ft 8 in | 2.15 m to 6 m

Weight: 2.24 lb/ft | 3.34 kg/m

Secondary moment Ix (cm⁴): 3.34 kg/m

Secondary moment Iy (cm⁴): 25.05

Section modulus Z+x (cm³): 224.82

Section modulus Z-x (cm³): 11.9

Section modulus Z+y (cm³): 11.9

Section modulus Z-y (cm³): 26.8

Core in anodized aluminum alloy: A6063S-T5 Serie 6000

Coefficient of Thermal Expansion (20-100°C):

23.4 µm/m/°C

Modulus of Elasticity: 68.9 GPa

Max Tensile Strength: 186 Mpa

Carbon Footprint:

924.35

Norms and certificates:

WPC : 1.54 kg CO₂ /Kg

Profile : 9.005 kg CO₂ /Kg



Teak



Limba



Rosewood



Wenge



Bilinga




Carbon



Ivory



Any color on request



Technical specifications, dimensions in mm		Wood hybrid system WHS		Type 1.0
Weight (lbs/ft)	-	11.93	Soleo 6032	
Cross section, secondary moment Ix (cm ⁴)	25.05	11.93		
Cross section, secondary moment Iy (cm ⁴)	224.82	26.84		
		35.55		